

DOMAMID® XS 66G50H1

Polyamide 66 alloy, 50% glass fiber, heat stabilized
preliminary datasheet

27.02.2016

TYPICAL PROPERTIES	CONDITION	STANDARD	UNIT	VALUE
PHYSICAL				
Density		ISO 1183	[g/cm ³]	1,57
Moisture absorption	T=23°C / 50%RH	ISO 62	[%]	1,4
Water absorption	T=23°C / sat.	ISO 62	[%]	4
RHEOLOGICAL				
Melt Volume Rate (MVR)	5Kg	ISO 1133	[cm ³ /10 min]	17
MECHANICAL				
				dam / cond.*
Tensile modulus	1 mm/min	ISO 527	[MPa]	18300 / 17200
Tensile stress at break	5 mm/min	ISO 527	[MPa]	265 / 245
Tensile strain at break	5 mm/min	ISO 527	[%]	3,0 / 3,0
Flexural modulus	2 mm/min	ISO 178	[MPa]	16000 / -
Flexural strength	2 mm/min	ISO 178	[MPa]	420 / -
Charpy unnotched	+23 °C	ISO 179/1eU	[kJ/m ²]	110 / 105
Charpy notched	+23 °C	ISO 179/1eA	[kJ/m ²]	15,5 / 15
THERMAL				
Melting point	DSC	ISO 11357-1	[°C]	262
Heat Deflection Temperature (HDT-A)	1,80 MPa	ISO 75	[°C]	235
ELECTRICAL				
Volume resistivity		IEC 60093	[Ω·cm]	>1E12
BURNING BEHAVIOUR				
Flammability		UL 94	[Class]	HB

Test run at 23°C if not differently specified, DAM state (dry as moulded).

*: conditioned according to ISO 1110

PROCESSING CONDITIONS:

Drying temperature/time : 75-85°C / 2-4h (with dew point of dried air < -30 °C)
 Recommended melt temperature : 280-305 °C
 Recommended mould temperature : 70-100 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.